



ROUND CORNER FITTING IN TPO




**All technical properties indicated are average values typical of the raw material used for the production, and they are not specifications. All information contained in this document only gives a generic description of the material used.*

Technical data sheet for TPO			
Typical Physical-Mechanical Properties	Method	u.m.	Values
Weight density	ISO 1183-1	g/cm ³	0,88
Hardness	ISO 868	Shore D	41
Tensile strain at Break	ISO 527-1, -2	%	400
Tensile stress at Break	ISO 527-1, -2	MPa	10
Melt flow rate	ISO 1133-1	g/10'	2.8



ROUND CORNER FITTING IN TPE L 500




**All technical properties indicated are average values typical of the raw material used for the production, and they are not specifications. All information contained in this document only gives a generical description of the material used.*

Technical data sheet for TPE			
Typical Physical-Mechanical Properties	Method	u.m.	Values
Weight density	ISO 1183	g/cm ³	1.02
Hardness	ISO 868	Shore D	52
Tensile strength	ISO 37	MPa	12.5
Melt Flow Index	ISO 1133	g/10'	70
Tear Strength	ISO 34	kN/m	62



SQUARE CORNER FITTING IN PVC



**All technical properties indicated are average values typical of the raw material used for the production, and they are not specifications. All information contained in this document only gives a generic description of the material used.*

Technical data sheet for PVC			
Typical Physical-Mechanical Properties	Method	u.m.	Values
Weight density	ISO 1183	g/cm ³	1,35
Hardness	ISO 868	Shore A	90
Tensile strength	ISO 527	N/mm ²	≥ 14,5
Breaking strain	ISO 527	%	≥ 200



ROUND CORNER FITTING IN PVC L 500




**All technical properties indicated are average values typical of the raw material used for the production, and they are not specifications. All information contained in this document only gives a generic description of the material used.*

Technical data sheet for PVC			
Typical Physical-Mechanical Properties	Method	u.m.	Values
Weight density	ISO 1183	g/cm ³	1,35
Hardness	ISO 868	Shore A	90
Tensile strength	ISO 527	N/mm ²	≥ 14,5
Breaking strain	ISO 527	%	≥ 200



SQUARE CORNER FITTING IN EPDM




**All technical properties indicated are average values typical of the raw material used for the production, and they are not specifications. All information contained in this document only gives a generic description of the material used.*

Technical data sheet for EPDM			
Typical Physical-Mechanical Properties	Method	u.m.	Values
Weight density	ISO 1183	g/cm ³	0.95
Shore A hardness	ISO 868	-	81
Melt Volume Rate	ISO 1133	g/10mi	1.5



ROUND CORNER FITTING IN EPDM



** All technical properties indicated are average values typical of the raw material used for the production, and they are not specifications. All information contained in this document only gives a generic description of the material used.*

Technical data sheet for EPDM			
Typical Physical-Mechanical Properties	Method	u.m.	Values
Weight density	ISO 1183	g/cm ³	0.95
Shore A hardness	ISO 868	-	81
Melt Volume Rate	ISO 1133	g/10mi	1.5