Benamor Blend

Size	65mm
Water Absorption	12%
Compressive Strength	20N/mm²
Durability	F2
Bricks per pack	640
Pack Weight	1.30T
Salt Classification	S2
Dimensional Tolerance	T2
Dimensional Range	R2



TBS
Traditional Brick & Stone

Facebook: traditionalbrick
LinkedIn: Traditional Brick & Stone
Instagram: tbsbrick
Pintrest: tradbrick

www.traditionalbrickandstone.co.uk

Traditional Brick & Stone Ltd
Park View House
Bow Street
Rugeley
Staffs
WS15 2DG

T: 01889 574466 F: 01889 227438
sales@traditionalbrickandstone.co.uk