Vapour Permeable Roofing Underlay

DuPont™ Everon™

Strong enough for UK weather. Smart enough for your budget. Backed by DuPont for 10 years.



- **A DuPont breather membrane** – airtight, ~130 g/sqm, high water column ensuring watertightness even under heavy rain, Fire Class E, 10-year DuPont warranty.
- **Patented Technology** – a unique product with high acceptance among roofers across the UK*.
- **Watertightness** – Up to 7m water column according to EN ISO 811.
- **Robust mechanicals** – 150/180 N nail tear resistance, 250/200 N/50mm tensile strength.
- **Installer-friendly format** – 1m × 50m rolls, lightweight, printed grid improves cutting accuracy and alignment.
- **Weather-ready spec** – up to 3 month UV resistance.

Key benefits:

- **Quality at a mid-tier price** for everyday roofs.
- **Trusted brand and technical backing** from the DuPont technical enquiries team, reducing callback risk.
- **Faster, easier installation** thanks to lightweight handling and the cutting grid.
- **Fits mainstream UK roofing jobs** – new builds, refurbishments, and light commercial.
- **100% recyclable** made from one material – easy to recycle.

* During a trial, we gathered feedback from 16 roofers across various regions in the UK.

DuPont™ Everon™

Property	Method	Unit	Performance
Water vapour transmission (sd)	EN ISO 12572 (C)	m	0.03
Water tightness	EN 1928 (A)	class	W1
Water column	EN ISO 811	m	7
Reaction to fire	EN 13501	Euroclass	E
Mass per unit area	EN 1849-2	g/m²	130
Maximum tensile force (MD)	EN 12311-1	N/50mm	250
Elongation at max. tensile force (MD)	EN 12311-1	%	55
Maximum tensile force (XD)	EN 12311-1	N/50mm	200
Elongation at max. tensile force (XD)	EN 12311-1	%	50
Resistance to tearing MD (nail shank)	EN 12310-1	N	150
Resistance to tearing XD (nail shank)	EN 12310-1	N	180
Artificial ageing results	EN 1297 & EN 1296		
Watertightness	EN 1928 (A)	class	W1
Maximum tensile force (MD)	EN 12311-1	%	90
Elongation at max. tensile force (MD)	EN 12311-1	%	75
Maximum tensile force (XD)	EN 12311-1	%	90
Elongation at max. tensile force (XD)	EN 12311-1	%	75
Additional properties			
Wind uplift resistance (battened lap)	BS5534:2014 +A2:2018 Annex A	Zone	1-2

DuPont Performance Building Solutions
HERE
470 Bath Road
Amo's Vale
Bristol, UK
BS4 3AP

Contact Tel: +44 0117 452 9050
Option 1: Technical (Building Knowledge Centre)
Option 2: General Enquiries

Technical Enquiries: **Tyvek.construction@dupont.com**

Building Knowledge Centre
– Science you can build on –

The information provided herein is based on data DuPont believes to be reliable and reflects our current knowledge and experience with this pilot product at the time of preparation. As the product is in an evaluation phase, the information may be limited and subject to update as additional data becomes available. It is not intended as a substitute for any testing you may conduct to determine for yourself the suitability of our products and information for your particular purpose. The information applies only to the specific product as supplied by DuPont and may not fully reflect performance in combination with other materials, processes, or conditions, which can influence results. This information is provided at no charge for your convenience. While we aim to provide helpful and accurate information, DuPont makes no representations regarding completeness or suitability of use. **TO THE EXTENT PERMITTED BY APPLICABLE LAW**, DUPONT DE NEMOURS, INC. AND ITS AFFILIATES DISCLAIM ANY IMPLIED WARRANTIES, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. DuPont does not accept responsibility for outcomes resulting from use of this information or the pilot product.

©2026 DuPont. All rights reserved. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ℠ or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

Form number 40-D101454-GB-0826 CDP