



Description

QUICK-STEP® KIT is a one-pack, acrylic sealant, remaining permanently flexible with high resistance against ageing and temperatures. **QUICK-STEP® KIT** can be painted when vulcanized.

Application

Instant adhesion on all clean and dry surfaces. When diluted with water it can be used as a sealant primer (2/3 of water, 1/3 of **QUICK-STEP® KIT**).

QUICK-STEP® KIT can be used on all porous surfaces such as, brick, concrete, wood, etc.

QUICK-STEP® KIT can also be applied for joints between windows, walls, doors, and window- ledges, etc. Suitable for joints with moderate movement (maximum 15%).

Processing Temperature

Between +5°C and + 40°C.

Surfaces

All surfaces should be dry, clean and free from dust or grease. When necessary, degrease with alcohol or ethanol. If necessary, use a primer. It is recommended that adhesion tests are carried out to determine the suitability of the product for its application (If needed, contact our technical services).

Finishing

Smoothen out with a solution of soap (before skinning starts).

Cleaning

With water before it is dry.

Restrictions

QUICK-STEP® KIT should not be used on joints that will be exposed to water on a permanent basis. Protect against frost. Should not be used as kit for windows. Do not apply when there's a risk of rain or frost.

Shelf life

The data on this sheet have been drafted according to the last state of the laboratory data. Technical characteristics can be changed or adapted. We are not responsible in case of incompleteness. Before usage, one needs to ensure that the product is suitable for its application. Therefore, tests are necessary. Our general conditions apply.

Min. 12 months if kept in the original packing and stored in cool and dry conditions. Store frost-free.

Packing

310 ml tube

Method of use

QUICK-STEP® KIT vulcanizes by evaporation of water. As long as less than 90% of the joints are vulcanised, a maximum movement of 5% is possible.

Safety

Keep out of reach of children. Wear protective clothing. Work under local exhaust/ventilation. Keep container tightly closed. Keep away from ignition sources/sparks.

In case of contact with eyes: rinse immediately with plenty of water for 15 minutes. In case of contact with skin: wash immediately with lots of water (15 minutes) and seek medical advice. Keep away from food until the product is hardened out. In case of accident or if you feel unwell, seek medical advice. Consult our safety data sheet.

Technical agreement

Société Nationale du Joint Français: SNJF code 75.

PROPERTIES

Unvulcanised sealant

Basis	Acrylic sealant
Vulcanisation system	Vaporize, H2O
Skimming time (23°C and 50 % R.H.)	70 min
Curing speed (23°C and 65 % R.H.)	0.5 mm/day
Density (ISO 1183)	1.68 g/ml

Vulcanised sealant

Hardness shore (ISO 868)	15
Elastic recovery (ISO 7389)	< 50%
Maximum permissible distortion	15%
Modulus at 100% elong. (ISO 8340)	0,08 N/mm ²
% elongation at break (ISO 8339)	> 250 %
Temperature resistance	-30°C / + 100°C

The data on this sheet have been drafted according to the last state of the laboratory data. Technical characteristics can be changed or adapted. We are not responsible in case of incompleteness. Before usage, one needs to ensure that the product is suitable for its application. Therefore, tests are necessary. Our general conditions apply.