

# A Cut Above.

Proudly made in the **UK** for almost **30** years, **Roofshield®** is the real deal in air and vapour permeable roofing membranes. Super strong, durable, **the original**, this construction gem can withstand anything nature throws its way. Now available at a more competitive price than ever before.



 **Roofshield®**

Forever Original

# Benefits

## Vapour Permeability

With a vapour resistance of 0.065 MNs/g and an Sd-value of 0.013m, Roofshield stands out as one of the most vapour-permeable membranes available.

## BBA Certification

Fully certified for both non-ventilated warm or cold roof applications since 1996, Roofshield maintains its position as the first membrane certified for use in cold non-vented roofs.

## Air Permeability

Facilitating air movement and moisture diffusion, Roofshield prevents condensation, dealing adeptly with higher moisture levels during building drying periods.

## NHBC Acceptance

With a certified air permeability of 34.4m<sup>3</sup>/m<sup>2</sup> h.50Pa, Roofshield eliminates the need for additional high-level ventilation on NHBC-approved projects, ensuring consistent specifications across diverse projects.

## Uniform Airflow

Roofshield's air permeability ensures more consistent airflow through non-ventilated roofs compared to roofs ventilated per BS5250, without the need for elaborate ventilation hardware.

## No Vapour Control Layer (VCL) Required

Uniquely, the BBA explicitly states that a vapour control layer is unnecessary for non-ventilated cold-pitched roof constructions using Roofshield.

## Water Resistance

Rated W1 under EN13859-1, Roofshield can endure a water column of over a meter without leakage, providing temporary weather protection to the building envelope for up to 3 months when exposed.

## BS5534 Compliance

Independently tested and compliant across the UK, Roofshield, without the need for high-level ventilation or a vapour control layer remains the simplest and most cost-effective method to meet regulatory standards.

Test	Method	Roofshield®
Mass Per Unit Area (g/m <sup>2</sup> )	EN 1849-2	196 g/m <sup>2</sup>
Wind Zone		1-5 <sup>1</sup>
Reaction to Fire	EN 11925-2	Class E
Water Vapour Resistance (Sd)	EN ISO 12572	0.013 m
Air Permeability (50 Pa)	EN 12114	≥34.4 m <sup>3</sup> /m <sup>2</sup> .hr50Pa
Water Penetration	EN 1928	Class W1 before & after ageing
Tensile Strength (N/5cm)	EN 12311-1	Before ageing MD 390 CD 230
		After ageing MD 330 CD 190
Elongation (%)	EN 12311-1	Before ageing MD 55 CD 75
		After ageing MD 40 CD 60
Tear Resistance (N)	EN 12310-1	MD 230 CD 275
Flexibility at low temperature	EN 1109	No cracking at minus 60°C

MD = machine direction, CD = cross/transverse direction

<sup>1</sup> see technical datasheet



## All products are manufactured under BS EN ISO 9001.

Don & Low reserves the right to change specifications or other product information. Don & Low accepts no responsibility or liability for information provided by third parties. No warranties, accepts or implied, are offered regarding the suitability of any product for your use, as site conditions and customer requirements vary. Should you require further information, please contact us. Products are sold subject to the seller's terms and conditions of sale. No warranty or immunity is offered against infringement of patents or other intellectual property rights. ©Don & Low Limited, 2024. The intellectual property in the products is owned and protected by Don & Low or its licensors.