

WRAPTITE

AIR BARRIERS

PRODUCT: Wraptite Self Adhesive Air Barrier
COMPOSITION: Three layer Polypropylene Film Laminate with Self Adhesive Coating
STANDARDS: EN 13859-2:2010 Underlay for Walls: System 3
NOTIFIED BODY: Eurofins Expert Services OY 0537 / RISE 0402

Physical Properties	Test Method	Mean results
Basis weight	Electronic Weigh Scale	292 g/m ² ± 15g/m ²
Reaction to Fire	EN 11925-2 BS EN 13501-1	Class B, s1, d0*
Water Vapour Resistance Sd	EN 12572	0.039m (-0.015m / +0.01m)
Water Penetration - Before Ageing	EN 1928 : 2000 (Method A)	Class W1 (before ageing) Class W1 (after ageing)
Tensile Strength	EN 12311-1	Mean MD 417N/50mm Mean XD 252N/50mm
Tear Resistance	EN 12310-1	Mean MD 412N Mean XD 286N
Flexibility at Low Temperature (EN 1109)	No Cracks at -40°C	N/A

*tested over 12mm Calcium Silicate Board as per BS EN 13238:2010
 All tests carried out to EN 13859-2 standard


Manufactured By:

The A. Proctor Group Ltd.
 The Haugh
 Blairgowrie
 United Kingdom
 PH10 7ER

Telephone: +44(0)1250 872261
Fax: +44(0)1250 872727
Web: www.proctorgroup.com

Signed for and on behalf of The A. Proctor Group Ltd.

Name:



Position: Technical Director

Place: The Haugh, Blairgowrie Date: 19/1/22



Download a brochure from
 our website...

www.proctorgroup.com

contact@proctorgroup.com | +44 (0) 1250 872261

Revised December 2021

