

# Technical Data

## PURAFLEX 40

High Modulus P.U Hybrid Based Adhesive And Sealant



### Description

PURAFLEX 40 is a high modulus, one component, polyurethane hybrid based sealant and adhesive that remains permanently elastic and has good adhesion to most substrates.

### Benefits

- Excellent chemical resistance.
- Excellent resistance to solvents when cured.
- Bonds to concrete, wood, metal, aluminium, polyester, glass, uPVC, stone, ceramics, etc.
- Over paintable with gloss and emulsion paints - preliminary test required before use.

### Recommended For

Sealing and bonding metal panels and trim. Expansion joint sealing in concrete panels, floor joint and road and bridge construction. Sealing in applications subject to vibration and mechanical abrasion. Marine applications - provides resistance to salt water. Multitude of sealing and bonding applications in the automotive and engineering markets. Bonding in container fabrication.

High traffic floor joints such as those found in garage forecourts, warehouse, factory floors, sports arenas, shopping centres etc.

### Specification Compliances

It is resistant to most solvents and when cured and can be over painted with oil and latex paints.

It is specifically designed as an easy flow flooring grade for all concrete saw cuts and floor slab expansion joints, where abrasion resistance is required.



### Available in

C3 Cartridges and 600ml Foil Pack in the following colours:

White  
Black  
Grey

### Storage

Store in cool dry conditions between +5°C and +25°C.

### Shelf Life

12 months from date of manufacture.

## PURAFLEX 40

High Modulus P.U Hybrid Based Adhesive And Sealant

### Health & Safety

Data sheet available to professional user upon request.

### Joint Dimensions

Joint depth should never exceed width. If so use EVERBUILD FIX AND FILL FOAM, EVERBUILD JOINT BACKER ROD or BOND BREAKING TAPE in cases where there is not enough depth to use Backer Rod.

Furthermore, ensure that the joint design only permits adhesion to two surfaces, as three sided adhesion will impair flexibility.

### Surface Preparation

All surfaces must be clean, dry and dust free. All loose or flaking surface coatings, and old sealant and mastic joints, should be removed before application. Glass, metal and aluminium should be cleaned with a proprietary solvent cleaner prior to application for optimum adhesion. When using solvents, always ensure adequate ventilation. Avoid heat, sparks and open flames. Observe and follow all precautions listed on the solvent container label.

### Specific Data

Base:	Polyurethane Hybrid
Curing System:	Moisture Cure
Skin Formation	10-30Mins at 20°C 65% relative humidity
Cure Time:	4mm per 24 hours
Hardness:	50 (+/-5) Shore A
Shrinkage:	<3%
Specific Gravity:	Approx 1.45-1.5
Service Temperature:	-40°C to 90°C
Application Temperature:	5°C to 30°C
Elastic Recovery:	>90%
Elongation at Break:	400%
Elasticity Modulus 100%:	0.94N/mm <sup>2</sup>
Breaking Strength:	1.7N/mm <sup>2</sup>
Resistance to Acids/Bases/Solvents:	Average. Mild acids/bases at < 10% concentration
Paintability	Water Based - Yes Solvent Based - Trial Necessary

### Movement Factors

Flexibility +/- 20%.

### Joint Width Calculation

Joint widths are calculated as in BS6213:

$$\text{Width} = \frac{M \times 100}{F} + M$$

Where M = movement and F = movement accommodation Factor

### Coverage

Joint size in mm	Litre per metre run	Metre per 310ml tube
5 x 5	0.025	12.4
5 x 10	0.050	6.2
10 x 10	0.1	3.2
15 x 10	0.15	2.1
20 x 10	0.2	1.6

### Primer

On porous substrates like concrete use sealant primer P1.

### Limitations

- Not for use on substrates that may bleed oils, solvents or plasticisers.
- Do not use on bitumen or asphalt.
- Do not use for potable water tanks.
- Yellowing can occur in predominantly dark conditions

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.